

**Description** PEVIKON™ P11 is a fine particle paste making vinyl chloride homopolymer produced by the PEVIKON™ process. It gives low viscosity pastes with Newtonian flow, good foam properties and high mineral filler acceptance.

**Applications** PEVIKON™ P11 is recommended for base coat, top coat and foam in artificial leather and wall coverings. Due to the low viscosity it is suitable for semi rigid foams and due to the low sieve residue it is suitable for dip impregnation. PEVIKON™ P11 performs also well in high speed coatings e.g. Reverse Roll Coater.



**Typical Properties**

Property	Unit	Value	Method
K-value		68	ISO 1628-2
Viscosity number	cm <sup>3</sup> /g	116	ISO 1628-2
Wet sieve retention (Retained on 63 micron sieve)	g/kg	2	ISO 1624
Volatile matter	g/kg	4	ISO 1269

The properties data shown above have been obtained from laboratory tests on representative samples of PEVIKON™ P11. Although the values are typical, they are for guidance only, and must not be used as a basis for specifications.

PEVIKON™ is a trade mark, the property of INOVYN ChlorVinyls Limited.

©INOVYN 2015. [www.inovyn.com](http://www.inovyn.com)



## PEVIKON™ P11

page 3/3

Customers are reminded that European Regulation 2011/10/EC requires that plastics materials and articles intended to come into contact with foodstuffs must not contain vinyl chloride monomer in a quantity exceeding 1 mg per kilogram in the final food contact product. Also, this regulation states that articles must not pass onto foodstuffs, which are in contact with such materials and articles, any vinyl chloride detectable by a method complying with the requirements of EU Regulation 882/2004/EC. In the experience of INOVYN, compositions based on polymer described in this literature will comply with these requirement when processed in accordance with best known practice.

Furthermore, additives, which may be added to INOVYN polymer to produce compositions are subject to additional regulations with regard to food contact.

Note: It is the responsibility of the customer and producer of the end product to ensure that the final material or article complies with all relevant regulations.

INOVYN's products are supplied only on the strict understanding that the customer and the producer of the end product will ensure that the regulations have been complied with. If guidance is required regarding the use of PEVIKON™ Polymers in Food Contact, users should seek assistance from the Customer Service Groups listed below.

Information contained in this publication (and otherwise supplied to users) is based on our general experience and is given in good faith, but we are unable to accept responsibility in respect of factors which are outside our knowledge or control. The information supplied in this publication relates to prime quality products only. Users of PEVIKON™ polymers should consult the appropriate INOVYN Health and Safety literature which is available from the addresses below.

July 2015

### INEOS ChlorVinyls Customer Service Groups

*for Germany, Austria, Switzerland,  
Benelux, France and Spain*

#### INOVYN Schkopau GmbH

Inhausersieler Straße 25  
26388 Wilhelmshaven  
Germany  
Tel. +49 4425 98-01  
Fax +49 4425 98-2408  
csg.germany@inovyn.com

*for UK and Ireland*

#### INOVYN ChlorVinyls Limited

Runcorn Site HQ, South Parade  
PO Box 9, Runcorn, Cheshire WA7 4JE  
United Kingdom  
Tel. +44 1928 516687  
Fax +44 1928 516688  
sharon.jones@inovyn.com

*for Norway, Sweden, Denmark, Finland, Russia,  
E. Europe, Italy and Greece*

#### INOVYN Sverige AB

SE-444 83 Stenungsund  
Sweden  
Tel. +46 303 87500  
Fax +46 303 87723  
logistics.ste@inovyn.com

### INEOS ChlorVinyls Business Centre

#### INOVYN ChlorVinyls Limited

Runcorn Site HQ, South Parade  
PO Box 9, Runcorn, Cheshire WA7 4JE  
United Kingdom  
Tel. +44 1928 516687  
Fax +44 1928 516688  
corpcom@inovyn.com