

Description PEVIKON™ P2310 is a paste-making vinyl chloride homopolymer produced by the PEVIKON™ process. It gives very high viscosity pastes with pseudoplastic and thixotropic flow behaviour. P2310 has good low temperature gelling properties.



Applications PEVIKON™ P2310 is recommended for applications such as automotive under-body coating and carpet backing, where low gelling temperature or short gelling time is required. It can in many cases replace copolymers. It is suitable in formulations with high plasticiser level or when pseudoplastic and thixotropic flow behaviour is requested.

Typical Properties

Property	Unit	Value	Method
K-value		61	ISO 1628-2
Viscosity number	cm ³ /g	90	ISO 1628-2
Wet sieve retention (Retained on 63 micron sieve)	g/kg	4	ISO 1624
Volatile matter	g/kg	4	ISO 1269

The properties data shown above have been obtained from laboratory tests on representative samples of PEVIKON™ P2310. Although the values are typical, they are for guidance only, and must not be used as a basis for specifications.

PEVIKON™ is a trade mark, the property of INOVYN ChlorVinyls Limited.
© INEOS ChlorVinyls 2011. www.ineoschlorvinyls.com



PEVIKON™ P2310

page 3/3

Customers are reminded that European Regulation 2011/10/EC requires that plastics materials and articles intended to come into contact with foodstuffs must not contain vinyl chloride monomer in a quantity exceeding 1 mg per kilogram in the final food contact product. Also, this regulation states that articles must not pass onto foodstuffs, which are in contact with such materials and articles, any vinyl chloride detectable by a method complying with the requirements of EU Regulation 882/2004/EC. In the experience of INOVYN, compositions based on polymer described in this literature will comply with these requirement when processed in accordance with best known practice.

Furthermore, additives, which may be added to INOVYN's polymer to produce compositions are subject to additional regulations with regard to food contact.

Note: It is the responsibility of the customer and producer of the end product to ensure that the final material or article complies with all relevant regulations.

INOVYN's products are supplied only on the strict understanding that the customer and the producer of the end product will ensure that the regulations have been complied with. If guidance is required regarding the use of PEVIKON™ Polymers in Food Contact, users should seek assistance from the Customer Service Groups listed below.

Information contained in this publication (and otherwise supplied to users) is based on our general experience and is given in good faith, but we are unable to accept responsibility in respect of factors which are outside our knowledge or control. The information supplied in this publication relates to prime quality products only. Users of PEVIKON™ polymers should consult the appropriate INOVYN Health and Safety literature which is available from the addresses below.

July 2015

INEOS ChlorVinyls Customer Service Groups

INEOS ChlorVinyls Business Centre

*for Germany, Austria, Switzerland,
Benelux, France and Spain*

for UK and Ireland

*for Norway, Sweden, Denmark, Finland, Russia,
E. Europe, Italy and Greece*

INOVYN Schkopau GmbH

Inhausersieler Straße 25
26388 Wilhelmshaven
Germany
Tel. +49 4425 98-01
Fax +49 4425 98-2408
csg.germany@inovyn.com

INOVYN ChlorVinyls Limited

Runcorn Site HQ, South Parade
PO Box 9, Runcorn, Cheshire WA7 4JE
United Kingdom
Tel. +44 1928 516687
Fax +44 1928 516688
sharon.jones@inovyn.com

INOVYN Sverige AB

SE-444 83 Stenungsund
Sweden
Tel. +46 303 87500
Fax +46 303 87723
logistics.ste@inovyn.com

INOVYN ChlorVinyls Limited

Runcorn Site HQ, South Parade
PO Box 9, Runcorn, Cheshire WA7 4JE
United Kingdom
Tel. +44 1928 516687
Fax +44 1928 516688
corpcom@inovyn.com